



Titacon TX940

RESIN : POLYACETAL RESIN

PRODUCT DESCRIPTION : HIGH IMPACT, TOUGHNESS, HIGH ELASTOMER FILLED.

Properties	Unit	method	Value
Color	-	-	Natural
specific gravity	g/cm ³	ISO 1183	1.32
Tensile strength Tensile Elongation	MPa	ISO 527-1,2	30 >100
Flexural strength Flexural modulus	MPa	ISO 178	30 850
Charpy impact strength(notched)	kJ/m ²	ISO 179/1eA	30
Heat Deflection Temperature(1.8MPa)	°C	ISO 75-1,2	70
Volume resistivity Surface resistivity	Ω•cm Ω	IEC 60093	1×10 ¹⁴ 1×10 ¹⁴
Flammability		UL 94	HB
Mold shrinkage	%	50x70x3 mmt	1.4~1.8
MOLDING CONDITION	°C	Drying Melt Temp. Mold Temp.	100x 3Hrs 170~200 60~100
	%	Inject. Press. Inject. Velocity	30~70 20~50

*All property values shown in this data sheet are the representative values and not minimum value of this material.