



Titacon NW901

RESIN : POLYACETAL RESIN

PRODUCT DESCRIPTION: CHEMICAL LUBRICATION, LOW WEAR/FRICTION,
LOW NOISE.

Properties	Unit	method	Value
Color	-	-	Nature
specific gravity	g/cm ³	ISO 1183	1.36
Tensile strength	MPa	ISO	52
Tensile Elongation		527-1,2	>30
Flexural strength	MPa	ISO 178	73
Flexural modulus			2200
Charpy impact strength(notched)	kJ/m ²	ISO 179/1eA	6
Heat Deflection Temperature(1.8MPa)	°C	ISO 75-1,2	85
Volume resistivity	Ω•cm	IEC 60093	1×10 ¹⁴
Surface resistivity	Ω		1×10 ¹⁵
Flammability		UL 94	HB
Mold shrinkage	%	50x70x3 mmt	2.0~2.4
MOLDING CONDITION	°C	Drying Melt Temp. Mold Temp.	100x 3Hrs 170~200 60~100
	%	Inject. Press. Inject. Velocity	30~70 20~50

*All property values shown in this data sheet are the representative values and not minimum value of this material.