



## Titacon EX210

**RESIN : POLYACETAL RESIN**

**PRODUCT DESCRIPTION : EXTRUSION GRADE, PERMANENT ANTI-STATIC,  
CARBON BLACK.**

Properties	Unit	method	Value
Color	-	-	Nature
specific gravity	g/cm <sup>3</sup>	ISO 1183	1.48
Tensile strength	MPa	ISO	45
Tensile Elongation		527-1,2	>20
Flexural strength	MPa	ISO 178	70
Flexural modulus			1750
Charpy impact strength(notched)	kJ/m <sup>2</sup>	ISO	7
		179/1eA	
Heat Deflection Temperature(1.8MPa)	°C	ISO	95
		75-1,2	
Volume resistivity	Ω•cm	IEC 60093	1×10 <sup>6</sup>
Surface resistivity	Ω		1×10 <sup>5~6</sup>
Flammability		UL 94	HB
Mold shrinkage	%	50x70x3	1.6~1.8
		mmt	
<b>MOLDING CONDITION</b>	°C	Drying	100x 3Hrs
		Melt Temp.	170~200
		Mold Temp.	60~100
	%	Inject. Press.	30~70
Inject. Velocity		20~50	

\*All property values shown in this data sheet are the representative values and not minimum value of this material.