



## Titacon ST220

**RESIN : POLYACETAL RESIN**

**PRODUCT DESCRIPTION : EXTRUSION GRADE, PERMANENT ANTI-STATIC, COLORABLE.**

Properties	Unit	method	Value
Color	-	-	Nature
specific gravity	g/cm <sup>3</sup>	ISO 1183	1.35
Tensile strength	MPa	ISO	39
Tensile Elongation		527-1,2	>30
Flexural strength	MPa	ISO 178	45
Flexural modulus			1700
Charpy impact strength(notched)	kJ/m <sup>2</sup>	ISO	13
		179/1eA	
Heat Deflection Temperature(1.8MPa)	°C	ISO 75-1,2	75
Volume resistivity	Ω•cm	IEC 60093	1×10 <sup>9</sup>
Surface resistivity	Ω		1×10 <sup>8</sup>
Flammability		UL 94	HB
Mold shrinkage	%	50x70x3 mmt	1.8~2.2
<b>MOLDING CONDITION</b>	°C	Drying	100x 3Hrs
		Melt Temp.	170~200
	%	Mold Temp.	60~100
		Inject. Press.	30~70
		Inject. Velocity	20~50

\*All property values shown in this data sheet are the representative values and not minimum value of this material.